Material Safety Data Sheet according to Regulation (EG) No. 1907/2006

Product Name: **P26**
Revision Date: 02.09.2010 Version: 1.0
Print Date: 06.09.2010

Company: Isola GmbH, D-52348 Düren

Product: P26

---

1. Chemical Characterisation:

Prepreg made from glass fabric and polyimide resin, MDA free (B-Stage)

---

2. Composition:

Glass fabrics: E-glass
Resin system: Polyimide resin

---

3. Hazards Identification:

Not classified as hazardous.

---

4. First-Aid Measures:

In case of cut and scratch caused by the material wash the wound with water and soap. Disinfection is useful.

---

5. Fire-Fighting Methods:

All kinds of fire fighting methods are useful, if possible do not use water.

In case of fire the following hazardous components can be produced:
carbon monoxide, carbon dioxide, oxides of nitrogen, hydrogen bromide and organic brominated compounds

---

6. Accidental Release Measures:

Be inapplicable

7. Storage and Handling:

Store in an air-conditioned room at a maximum temperature of 20 °C and a rel. humidity of 40 to 50 %. Cold room storage increases the storage stability of the prepreg.
Further information: see technical data sheet.

8. Exposure Control and Personal Protection:

Limits:

CAS-Number	Substance	List	Exposure Limit	Unit
Be inapplicable				

Personal Protection:

- Respiratory Protection:	suction system
- Hand Protection:	skin cream
- Eye Protection:	useful
- Body Protection:	
- Industrial Hygiene:	no eating, drinking or smoking; cleanness necessary.

9. Physical and Chemical Properties:

Appearance:	sheets or rolls
Colour:	brown
Odour:	odourless

Change of Condition:

- Boiling Point:	(°C)	not applicable
- Melting Point:	(°C)	at approx. 65 °C (softening)
- Curing:	(°C)	approx. 130 °C (DSC-Method 20 °C/min heating rate)
- Flash Point:	(°C)	not applicable
- Autoignition Temperature:	(°C)	not applicable
- Explosion Limits:	(Vol.-%)	lower: not applicable upper: not applicable
- Thermal Decomposition:	(°C)	at approx. 320 °C (Thermogravimetry 10 °C/min heating rate)
- Vapour Pressure:	(mbar) at 20 °C	not applicable
- Density:	(g/cm^3) at 20 °C	approx. 1.8 (after curing)
- Viscosity:	(mPa*s)	at room temperature not applicable
- Solubility in Water:		insoluble

10. Stability and Reactivity:

Conditions to avoid: Formation of dust in the working area, elevated temperature.
Reactivity: Curing at approx. 130 °C

11. Toxicological Information:

The dust occurring from cutting and drilling processes is in principle not toxic. Beginners may have skin irritations, however, there is a quick accustoming. Exceptionally skin allergies; this person should be employed elsewhere.

12. Ecological Information:

No data available

13. Disposal Considerations:

After curing: normal industrial waste in accordance with local regulations

14. Transport Information:

Road: no hazardous product
Ship: no hazardous product
Plane: no hazardous product

15. Regulatory Information:

EC Risk Phrases:

Not classified as hazardous

EC Safety Phrases:

Not classified as hazardous

16. Other Information:

The above mentioned data correspond to our present state of knowledge and experience. The safety data served as description of the product in regard to necessary safety measures. They do not guarantee the described chemical properties.

If you need further information please contact:
Dipl.-Ing. G. Czerny (Phone: +49-(0)2421-808-679; Fax: +49-(0)2421-808-8679)